

Bezeichnung der Verwendung im Gesamtsystem	Herstellerbezeichnung	Technische Maße / Dimension Gewicht / Festigkeit	Lieferant / DIN Nr.
Attachement loops	Nylon Webbing	7,0 g/m / breaking strength 110kg / 10mm spreads	Aqua Dynamiks, Sri Lanka
Brake attachements	Nylon Webbing	7,0 g/m / breaking strength 110kg / 10mm spreads	Aqua Dynamiks, Sri Lanka
Brake handhold	High Tanacity Poliester Yarn 20mm	23 g/m / 400 kg breaking strength	Aqua Dynamiks, Sri Lanka
Brake handhold attachement	High Tanacity Poliester Webbing 10mm	15 g/m / 300 kg breaking strength	Aqua Dynamiks, Sri Lanka
Brake handhold fixation	Press Button		Aqua Dynamiks, Sri Lanka
Brake main line LIROS TSL 380	LIROS TSL 380	2,2mm / 380kg	Rosenberger Tauwerke
Lines: Look at Lineconfiguration	LIROS DSL70 / DC100 / TSL140;190;280;380	Look lineconfiguration	Rosenberger Tauwerke
Belt direction	Stainless Steel	8g / Ø 3,8mm / breaking strength 800kg	Aqua Dynamiks, Sri Lanka
Lines lock	Stainless Steel	10g / Ø 3,5mm / breaking strength 750kg	Aqua Dynamiks, Sri Lanka
Top	NK40	42 g/m ² PA 6.6	Toray, Japan
Bottom	NK40 // Skytex 36	42 g/m ² // 36 g/m ² PA 6.6	Toray, Japan // Porcher Marine, NCV, France
Rips, Profile (with line-starting-point)	Skytex 32 hard finish	32 g/m ² , PA 6.6 HT, HF	Porcher Marine, NCV, France
Rips, Profile (without line-starting-point)	Skytex 27 hard finish	27 g/m ² , PA 6.6 HT, HF	Porcher Marine, NCV, France
V-Rips, V-Tapes	Skytex 32 hard finish	32 g/m ² , PA 6.6 HT, HF	Porcher Marine, NCV, France
Profilenose reinforcement	PPN - Nylon	2,2mm / 2,5mm Ø	Aqua Dynamiks, Sri Lanka
Riser	20mm Gurtband	21 g/m / 1000 kg breaking strength	Guth & Wolf, Germany
Reinforcement povit point A/B/C/D	180 Dacron	180 g/m ²	Aqua Dynamiks, Sri Lanka
sewing thread canopy	High Tanacity Poliester Yarn 150D/2	0,05 g/m ² / 2,9 kg breaking strength	Amann & Söhne GmbH, Germany
sewing thread lines	High Tanacity Poliester Yarn 150D/3	0,083 g/m ² / 3,2 kg breaking strength	Amann & Söhne GmbH, Germany